

888.496.3406 • dinsmoreinc.com • sales@dinsmoreinc.com • 1681 Kettering Street, Irvine, CA 92614

Inconel 718

TECHNOLOGY: DMLS

APPLICATIONS: Aero & Land Based Turbine Engines / Rocket & Space Application Components / Chemical & Process Industry Parts / Oil Well Petroleum, & Natural Gas Industry Parts

DESCRIPTION:

NickelAlloy IN718 is a nickel based heat resistant alloy in fine powder form. This kind of precipitationhardening nickel-chromium alloy is characterized by having good tensile, fatigue, creep and rupture strength at temperatures up to 700°C. 718 alloy has also outstanding corrosion resistance in various corrosive environments. In both as-built and age-hardened states the parts can be machined, spark-eroded, welded, micro shot-peened, polished and coated if required.

This material is ideal for many high temperature applications such as gas turbine parts, instrumentation parts, power and process industry parts etc. Material also possess excellent cryogenic properties and potential for cryogenic applications.

TECHNICAL DATA				
PROPERTY	ISO			
		AS BUILI	AINIS 5002	ANIS 5004
Ultimate Tensile Strength	6892	980 MPA	1400 MPA	1384 MPA
0.2% Proof Strength	6892	634 MPA	1150 MPA	1239 MPA
Elongation	6892	31 %	12 %	12 %
Hardness, Rockwell C	6508-1	30	47	43

Heat treatment procedure per AMS 5662: STEP 1. Solution Anneal at 980°C for 1 hour, air (/argon) cool. STEP 2. Ageing treatment; hold at 720°C 8 hours, furnace cool to 620°C in 2 hours, hold at 620°C 8 hours, air (/argon) cool.

Heat treatment procedure per AMS 5664: STEP1. Solution Anneal at 1065°C for 1 hour, air (/argon) cool. STEP 2. Aging treatment; hold at 760°C 10 hours, furnace cool to 650°C in 2 hours, hold at 650°C 8 hours, air (/argon) cool