

888.496.3406 • dinsmoreinc.com • sales@dinsmoreinc.com • 1681 Kettering Street, Irvine, CA 92614

RPU 70

TECHNOLOGY: DLS

APPLICATIONS: General purpose prototyping, end-use parts.

DESCRIPTION: Rigid Polyurethane is Carbon's most versatile rigid material family. It is used across a wide range of industries, including consumer products, automotive, and industrial. RPU 70 has a UL 94 HB flame resistance classification.

FEATURES: Moderate heat resistant. Tough.

Color Options: Black

TECHNICAL DATA

PROPERTY	ASTM	METRIC UNITS
Tensile Strength	D638M	45 ± 2 MPa
Modulus of Elasticity, Youngs Modulus	D638M	1,900 ± 200 MPa
Elongation Break (%)	D638M	100 ± 20 %
Flexural Strength	D790M	62 ± 9 MPa
Flexural Modulus	D790M	1,800 ± 300 MPa
IZOD Impact Strength (notched)	D256A	22 ± 1 J/m
Heat Deflection Temperature @ 0.45 MPa/66 psi, (°C)	D648	70 °C



